

 **ORIENTCERAMICA**



Zero Shine
EDITION 2025




MAMRI ANGUS

MARMI ANGUS

FL MARMI ANGUS ZG 600X1200 GR D

SIZE



30X120 AND 20X120 WILL BE PRODUCED ON DEMAND

SURFACE & FINISH



ZERO SHINE

AVAILABLE COLORS



Tile Faces



FACE 1



FACE 2

Colors shown in the catalogue are for reference only. Please check physical tile before buying.


ORIENT CERAMICA

MARMI VENETZ

MARMI VENETZ

FL MARMI VENETZ ZG 600X1200 GR D

SIZE



30X120 AND 20X120 WILL BE PRODUCED ON DEMAND

SURFACE & FINISH



ZERO SHINE

AVAILABLE COLORS



Tile Faces



FACE 1



FACE 2

Colors shown in the catalogue are for reference only. Please check physical tile before buying.

ORIENT CERAMICA




MARMI TREVES

MARMI TREVES

FL MARMI TREVES ZG 600X1200 WT L

SIZE



30X120 AND 20X120 WILL BE PRODUCED ON DEMAND

SURFACE & FINISH



ZERO SHINE

AVAILABLE COLORS



Tile Faces



FACE 1



FACE 2










FACE 3









FACE 4

Colors shown in the catalogue are for reference only. Please check physical tile before buying.

TECHNICAL DATA SHEET

Sr. No.	TECHNICAL CHARACTERISTICS	STANDARD TEST METHOD	INTERNATIONAL STANDARD	ORIENT CERAMICA	
1.		Length & Width	BS EN ISO 10545-2	+/-0.6%	+/-0.1%
2.		Thickness	BS EN ISO 10545-2	+/-5.0%	+/-3.0%
3.		Rectangle Squareness	BS EN ISO 10545-2	+/-0.6%	+/-0.2%
4.		Straightness of Sides	BS EN ISO 10545-2	+/-5.0%	+/-0.2%
5.		Surface of Flatness	BS EN ISO 10545-2	+/-0.6%	+/-0.2%
6.		Water Absorption	BS EN ISO 10545-2	+/-5.0%	< 0.1%
7.		Modulus of Rupture	BS EN ISO 10545-2	>= 35N/mm ²	>= 40N/mm ²

TECHNICAL DATA SHEET

Sr. No.		TECHNICAL CHARACTERISTICS	STANDARD TEST METHOD	INTERNATIONAL STANDARD	ORIENT CERAMICA
8.		Breaking Strength	BS EN ISO 10545-4	≥ 1300 N	+/-0.1%
9.		Resistance to Deep Abrasion	BS EN ISO 10545-7	≤ 175 /mm ³	+/-3.0%
10.		Resistance to Thermal Shock	BS EN ISO 10545-9	No visible defects	+/-0.2%
11.		Frost Resistance	BS EN ISO 10545-12	No visible damage	+/-0.2%
12.		Resistance to Chemicals	BS EN ISO 10545-13	No visible defects	+/-0.2%
13.		Color Resistance to UV Lights	DIN 51094	No change in color	$< 0.1\%$

ORIENT CERAMICA

The Only **Grès Porcelain** Tile Manufacturer in Pakistan.

